

SGS Egypt Free Zone Laboratories Unit.
Minerals Laboratory

La Pace International For Trade Co.

Report of Analysis: EG13-00464.003

Ref: MIN13-1070 (1-3)

SAMPLE TYPE : One sample of Salt handed over to us SAMPLED BY : Ex. Client

ANALYSED : 18/06/2013 RECEIVED : 17/06/2013

COMPLETED : 18/06/2013

SAMPLE COMMENT : One sample of Salt approx. 250 g packed in a plastic
Plastic bag not sealed with sgs seal.
The sample was submitted and identified by external client.

REPORT COMMENT : ROCK SALT (W)

TRACIBLE TO:-

1-Oven # Inv. MN 003

2-Muffle Furnace # Inv. MN 004

3-Analytical Balance # Inv. MN 001

| Test Name | RESULT | UNIT | Method |
|----------------------------|--------|------|---------------|
| Moisture | 0.04 | % | ASTME534/2003 |
| Purity(as Sodium Chloride) | 99.480 | % | ASTME534/2003 |
| Water Insoluble Matter | 0.26 | % | ASTME534/2003 |
| SO4 | 0.17 | % | ASTME534/2003 |
| Ca | 0.02 | % | ASTME534/2003 |
| Mg | 0.04 | % | ASTME534/2003 |
| CaSO4 | 0.07 | % | ASTME534/2003 |
| MgSO4 | 0.15 | % | ASTME534/2003 |
| MgCl2 | 0.04 | % | ASTME534/2003 |

** End of Report **

AUTHORISED SIGNATORY

Ahmed Zaki-Minerals lab Manager

1806201313070000001274

Page 3 of 3

This report is issued by the Company under its General Conditions for Inspection and Testing Services (copy available upon request). The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale. Stipulations to the contrary are not binding on the Company. The Company's responsibility under this report is limited to proven negligence and will in no case be more than ten times the amount of the fees or commission. Except by special arrangement, samples, if drawn, will not be retained by the Company for more than three months. The information stated in this report (or certificate) is derived from the results of inspection or testing procedures carried out in accordance with the instructions of our Client, and/or our assessment of such results on the basis of any technical standards, trade custom or practice, or other circumstances which should in our professional opinion be taken into account. This report reflects results only of the standards or procedures identified to tests conducted & are limited to the samples tested. The test document cannot be reproduced in any way, full context or, partial without the prior approval in writing of the SGS Egypt lab.